티그·미그(TIG·MIG)용접재료

AWS ER308H

T-308H

Typical applications

Welding of high carbon 18%Cr-8%Ni stainless steels (AISI 304H) It provides better weldability together with excellent corrosion resistance.

Typical chemical composition of rod (%)

С	Si	Mn	Ni	Cr
0.05	0.42	2.06	9.80	19.80

Typical mechanical properties of all-weld-metal

Shielding Gas	T·S	El	IV	
Sillelaing das	N/mm²{kgf/mm²}	(%)	(J)	
Ar	590 {60}	42	-	

Package

Dia. (mm)	1.2	1.6	2.0	2.4	2.6	3.2	4.0
Weight.(kg)	5						
Length. (mm)				1000			

Approved by