T-430

AWS ER430 JIS Y430

Typical applications

Welding of ferrite stainless alloys of the 17%Cr types (AISI 430, dissimilar steels) It is suitable for automotive exhaust fabricators such as front pipe, bellows, flange.

Typical chemical composition of rod (%)

С	Si	Mn	Ni	Cr
0.02	0.33	0.44	-	16.60

Typical mechanical properties of all-weld-metal

Shielding Gas	T ⋅ S N/mm²{kgf/mm²}	EI (%)	Remark					
Ar	500 {51}	33	PWHT:745℃ ×1hr					
Package								
Dia. (mm)	1.2 1.6 2.0	2.4	2.6 3.2 4.0					
Weight.(kg)	5							
Length. (mm)	1000							

Approved by